

cont
B2
Sub
CD
wherein said emulsion is obtainable by applying a shear force corresponding to a shear rate of 10,000 s⁻¹ or more to a mixture of component (A), component (B) and component (C).

2. (Twice Amended) The oil-in-water emulsion according to Claim 1 having a light transmittance at 550 nm of 50% or more.

3. (Twice Amended) The oil-in-water emulsion according to Claim 1 having emulsion particles with an average particle size [of the particles in the emulsion ranges] ranging from 0.01 to 0.2 μm.

B2
6. (Twice Amended) The oil-in-water emulsion cosmetic according to Claim 1, wherein said emulsion is obtainable by applying a shear force corresponding to a shear rate of 1,000,000 s⁻¹ or more to a mixture of the component (A), component (B) and component (C).

7. (Twice Amended) The oil-in-water emulsion according to Claim 2, wherein said emulsion is obtainable by applying a shear force corresponding to a shear rate of 1,000,000 s⁻¹ or more to a mixture of the component (A), component (B) and component (C).

B3
15. (Amended) The oil-in-water emulsion of Claim 1 that is produced using a high-pressure commercial emulsifier that applies a shear force corresponding to a shear rate of 10,000 s⁻¹ or more.

B3
Sub
CD
20. (Amended) A method of making an oil-in-water emulsion comprising :

(A) a hydrophilic surface active agent,

(B) an oily component and

(C) water,

wherein the weight ratio of component (B) is more than 10 based on 1 of the component (A) comprising: